



Shed & Fence Coat

Technical Data Sheet

1. Description

Voller Shed & Fence coat is specially formulated to give long lasting protection to wooden sheds and fencing. Its fast-drying synthetic formulation prevents rot, decay and weathering of new and existing wooden products. Easy application by brush, roller or sprayer.

2. Properties:

- Great adherence to wooden substrates
- High coverage
- Long lasting protection
- Protects against rot & decay
- Good colour and gloss retention
- Excellent weathering resistance
- Great hardness and flexibility
- Very easy application (ideal for spray, brush or rolled application methods)
- lead & chromate free

3. Recommended uses:

Specially formulated for long lasting protection of exposed wooden surfaces in outdoor environments to prevent rot, decay and weathering of wooden sheds and Fencing.

4. Presentation Colours:

Black, Dark Oak, Red Cedar, Green, Teak, Urban Grey, Clear

Available units: 5, 20 and 200 containers

NB: Special order colours available on request*

5. Technical Characteristics:

- | | |
|--------------------------------|---|
| • Nature | Modified Alkyd resin |
| • Pigments | Lightfast pigments |
| • Solvents | Aromatics and ketones |
| • Propellant | Hydrocarbons, rich in C3 y C4 |
| • Density | 0.98 ± 0.02 gr./cc (Colour dependent) |
| • Viscosity | 16 – 18 seg. (Ford Cup Nr. 4, 20°C) |
| • % solids in weight | 36 ± 5 % (Theoretical value) |
| • VOC | 600± 10 gr./l (Colour dependant) |
| • Gloss at 60° | > 90 |
| • Coverage: | 10 to 15m2 per litre (substrate dependant). |
| • Drying time at 20°C: | Superficial: 2 hours
Total: 4 hours
Recoating: within 1 hour or after 48 hours. |
| • Application temperature | 10 to 35°C |
| • Paint resistance to the heat | Recommended up to 90°C |

<ul style="list-style-type: none"> • Flammability • Pressure: • Cleaning • Life of the product 	<p>Extremely flammable</p> <p>3-4 bars at 20°C</p> <p>6-7 bars at 50°C</p> <p>Standard Thinners</p> <p>> 3 years</p>
<p>6. Application:</p> <ul style="list-style-type: none"> • Thoroughly mix the paint prior to application until a uniform consistency is achieved throughout the drum. (Ensure any heavier pigment settled at the bottom of the drum is reincorporated into the resin to ensure even coverage). • Ensure the surface is dry and clean prior to painting • Apply light even coats across the entire surface • Recoat within 1 hr if required or after 48hrs. • Cleaning solvent- Standard Thinners. 	
<p>7. Safety:</p> <ul style="list-style-type: none"> • Keep out of the reach of children • Store in a cool dry place • Use appropriate PPE when stirring or applying the product • Avoid direct contact with skin • Seek medical help in case of ingestion 	

For further information in the UK
& Ireland contact:

Polycolor LTD

92 Orchard rd.
Strabane
Co. Tyrone
BT82 9QU